

ALLOY : TIN-LEAD	MELTING RANGE	
	degrees F	degrees C
Sn63Pb37	361	183
Sn60Pb40	361-374	183-190
Sn55Pb45	361-397	183-203
Sn50Pb50	361-420	183-214
Sn45Pb55	361-440	183-225
Sn40Pb60	361-460	183-238
Sn35Pb65	361-477	183-247
Sn30Pb70	361-496	183-258
Sn25Pb75	361-514	183-268
Sn20Pb80	361-536	268-302
Sn10Pb90	514-576	268-302
Sn05Pb95	574-597	301-314

ALLOY : LEAD-FREE	MELTING RANGE	
	degrees F	degrees C
Sn96.5Ag3.5	430	221
Sn96Ag04	430-444	221-229
Sn95Ag05	430-473	221-245
100%Sn	450	232
Sn95Sb05	450-464	232-240
Sn99.3Cu0.7	440	227
Sn96.6Ag3.0Cu0.5	422-428	217-220
Sn95.5Ag3.8Cu0.7	422-430	217-221

ALLOY : OTHER	MELTING RANGE	
	degrees F	degrees C
Sn62Pb36Ag02	354-372	179-189
Sn60Pb36Ag04	354-475	179-246
Sn10Pb88Ag02	514-570	268-299
Sn05Pb93.5Ag1.5	565-574	296-301
Sn05Pb92.5Ag2.5	536	280
Sn43Pb43Bi14	291-325	144-163